

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**

**This Page Blank (uspto)**



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>7</sup> :</b> <b>C09D 11/02</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 00/42113</b> <b>(43) International Publication Date:</b> 20 July 2000 (20.07.00)												
<b>(21) International Application Number:</b> PCT/GB00/00062 <b>(22) International Filing Date:</b> 12 January 2000 (12.01.00) <b>(30) Priority Data:</b> <table border="0"> <tr> <td>9900654.6</td> <td>14 January 1999 (14.01.99)</td> <td>GB</td> </tr> <tr> <td>9901031.6</td> <td>19 January 1999 (19.01.99)</td> <td>GB</td> </tr> <tr> <td>9921394.4</td> <td>10 September 1999 (10.09.99)</td> <td>GB</td> </tr> <tr> <td>9921618.6</td> <td>14 September 1999 (14.09.99)</td> <td>GB</td> </tr> </table> <b>(71) Applicant (for all designated States except US):</b> REFLECTIVE TECHNOLOGY INDUSTRIES LIMITED [GB/GB]; Road One, Winsford Industrial Estate, Winsford, Cheshire CW7 3QQ (GB). <b>(72) Inventor; and</b> <b>(75) Inventor/Applicant (for US only):</b> SAGAR, Brian [GB/GB]; The Cottage, 42 Moseley Road, Cheadle Hulme, Cheadle, Cheshire SK8 5HJ (GB). <b>(74) Agents:</b> McNEIGHT, David, Leslie et al.; McNeight & Lawrence, Regent House, Heaton Lane, Stockport, Cheshire SK4 1BS (GB).		9900654.6	14 January 1999 (14.01.99)	GB	9901031.6	19 January 1999 (19.01.99)	GB	9921394.4	10 September 1999 (10.09.99)	GB	9921618.6	14 September 1999 (14.09.99)	GB	<b>(81) Designated States:</b> AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>
9900654.6	14 January 1999 (14.01.99)	GB												
9901031.6	19 January 1999 (19.01.99)	GB												
9921394.4	10 September 1999 (10.09.99)	GB												
9921618.6	14 September 1999 (14.09.99)	GB												
<b>(54) Title:</b> RETROREFLECTIVE INKS														
<b>(57) Abstract</b>  <p>The combination of ingredients, especially for use in the formulation of a one or two-pack retroreflective ink, comprising retroreflective elements, microbeads additional to said retroreflective elements and/or constituting said retroreflective elements at least in part, binder chemicals for attaching the retroreflective elements and microbeads to a substrate to which the ink is to be applied, and a coupling agent for coupling the microbeads and cross-linking the binder chemicals, the coupling agent being unreactive until the printing process is carried out.</p>														

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

## **RETROREFLECTIVE INKS**

This invention relates to retroreflective inks and methods for making them.

Retroreflective coating compositions have been the subject of numerous patents, for example US Patents 2 963 378, Palmquist *et al*, 3 099 637, 3 228 897 and 3 420 597, Nellessen, 3 535 019, Longlet *et al* and 4 103 060 and 4 263 345, Bingham *et al*. A retroreflective ink has been commercially available for a number of years, marketed by the 3M company, this product being available in dark grey and sold as a three pack system, comprising a binder dispersion system, a pack of hemispherically coated glass microspheres or beads and a coupling agent, which are mixed just prior to use.

One pack inks were proposed in WO 94/06869, M N Ellis and in EP 0 729 592, Reflective Technology Industries Limited and US 5 650 213, Reflective Technology Inc., which also disclose the incorporation of pigment. US 5 650 213 specified a range of pigment particle size which is what is, in fact, the usual range commercially available, and ranges of binder/bead and binder/(bead and pigment) volume ratios which are seemingly the ranges of choice to produce an ink which is printable by conventional screen printing techniques.

Problems associated with the performance of reflective coatings, especially in the convenient, one-pack form that does not require mixing just prior to printing, involve shelf life, washfastness and abrasion resistance. These key areas are interrelated - the binder system must be such as will not allow the beads to settle even over extended storage periods, and it must also not couple to the beads during that storage, yet it must, on printing, adhere the beads to the substrate in a reasonably washfast and abrasion

resistant manner while permitting the beads to be exposed appropriately to retroreflect light.

The severity of these problems may explain the sale by 3M of the three pack system and the fact that the inks produced according to US 5 650 213 are formulated solely for the production of printed fabric by the patentee Reflective Technology Inc. and not for sale to printers.

The present invention addresses these - and other - problems and provides long shelf life one pack retroreflective ink systems with good washfastness and abrasion resistance.

According to one aspect of the present invention there is provided the combination of ingredients, especially for use in the formulation of a one or two-pack retroreflective ink, comprising retroreflective elements, microbeads additional to said retroreflective elements and/or constituting said retroreflective elements at least in part, binder chemicals for attaching the retroreflective elements and microbeads to a substrate to which the ink is to be applied, and a coupling agent for coupling the microbeads and cross-linking the binder chemicals, the coupling agent being unreactive until the printing process is carried out.

A one-pack ink produced using the above combination of ingredients may have a storage life of not less than 3 months, preferably not less than 6 months and more preferably not less than 12 months when stored under ambient conditions (i.e. a temperature of about 20°C). Also such inks, when stored for prolonged periods of 3 months or more under ambient conditions, show no significant change in rheology while retaining adequate retroreflectivity properties and durability to laundering. Thus, a retroreflective one-pack ink in accordance with the invention may retain a viscosity of between 10 and 30 pascal after storage for not less than 3 months, preferably not less

than 6 months and more preferably not less than 12 months, and may also exhibit laundering durability such that retroreflectivity is not reduced by more than 40% (preferably by not more than 30% and more preferably by not more than 20%) when applied to a substrate in the form of a cotton, nylon or polyester and laundered for 5 cycles in accordance with ISO 6330, method 5A.

The coupling agent is usually one which is substantially unreactive at ambient temperature, namely 20°C. Typically the coupling agent is unreactive except at elevated temperature at which the printed substrate is cured, e.g. a temperature within the range of 60 to 200°C, e.g. 130 to 180°C.

The coupling agent may be rendered active by elevated temperature; however, we do not exclude the possibility that the coupling agent may be rendered active by other means such as exposure to UV light or other high energy radiation.

Typically the binder is polymeric and the coupling agent serves to couple the beads to the polymeric binder.

Viewed from another aspect, the invention resides in a one-pack or a two-pack retroreflective ink comprising microbeads in a liquid carrier medium including binder chemicals for attaching the microbeads to a substrate to which the ink is to be applied, the microbeads being incorporated in the carrier medium, and a coupling agent which couples the microbeads and cross-links the binder chemicals, characterised in that the coupling agent is not activated until the ink is printed.

The two-pack system comprises a separate pack for the coupling agent.

The ink may comprise retroreflective and/or non-retroreflective microbeads. Typically the proportion of microbeads which do not have a retroreflective coating constitute no more than 50% by volume of the total microbead content but may be up to 100% when reflective flakes are used in conjunction with microbeads to provide retroreflectivity.

The binder and coupling agent may be selected from, but is not limited to, the following combinations:

polyvinylidene chloride copolymer as binder and (3-aminopropyl) silanetriol and/or blocked 1, 6 hexamethylene diisocyanate trimer as coupling agent;

an acrylic copolymer as binder and (3-aminopropyl) silanetriol and/or blocked 1, 6 hexamethylene diisocyanate trimer as coupling agent; and

polyurethane as binder and blocked 1, 6 hexamethylene diisocyanate trimer as coupling agent.

The microbeads may have an aluminium coating, and may be pre-treated with a silicate before inclusion in the ink. They may for instance be pretreated with sodium silicate. They may be treated with a silane, especially a silane having a reactive group such as an amino group, which treatment may be after a silicate treatment and before inclusion in the ink. A suitable amino silane is bis-*[gamma*-(trimethoxysilyl) propyl] amine.

The ink may comprise pigment, and may, especially when comprising pigment, comprise non-retroreflective, which usually means un-metallised, microbeads. The pigment content is typically up to 5% by weight of the ink.



The microbeads may be pretreated before metallisation with stannous chloride.

The ink may be formulated - as to, e.g. viscosity, particle size - suitably for screen printing. The microbeads may have a median size in the range of 10 to 100 microns, e.g. 25 to 70 microns. Typically in the case of inks using metallised retroreflective microbeads, the median size is about 40 microns whereas in the case of inks using non-retroreflective microbeads in conjunction with other reflective elements such as reflective flake particles, the microbeads typically have a median size of about 60 microns.

The microbeads, whether retroreflective or not, are preferably composed of high refractive index glass, such as a titanium/barium based glass with a refractive index in the range of 1.8 to 2.2, e.g. about 1.9.

The ink may comprise a humectant, which may comprise urea and/or 2,3 propane diol, and may be water-based. It may comprise a buffer, to ensure an appropriate pH, such buffer, for example, comprising an ammonium phosphate buffer or a sodium phosphate buffer. A dispersant may also be included, as may a defoamer, a thickening agent, a cross-linking agent and a softening agent.

Other constituents that may be present in the ink may be selected from the group comprising carbon black; UV absorbing material; anti-scuffing agent, optionally a silicone or fluoropolymer; light spill-suppressing agent; anti-static agent and water repellant agent, optionally a silicone or fluoropolymer.

Non-water based inks may also be comprised within the invention. In this case, the need to protect the aluminium coating against attack in water-based media may be less important.

Surprisingly, having regard to the teaching of US 5 650 213, substantially better quality inks - in terms of reflectivity, washfastness, abrasion resistance and shelf life - are produced with binder to bead volume ratios equal to or less than 50%. Essentially, more beads can be attached using less obscuring binder, more firmly and more permanently than when the prior art binder to bead ratios are used.

For a screen printing ink, the viscosity is desirably equal to or less than 40 pascals, preferably between 10 and 30 pascals, at room temperature.

The invention also comprises a method for making a one-pack retroreflective ink comprising the steps of:

- making microbeads;
- suspending the microbeads in a liquid carrier medium;
- the liquid carrier medium comprising binder chemicals for attaching the microbeads to a substrate to which the ink is to be applied and a coupling agent which couples the microbeads and cross-links the binder chemicals, the coupling agent being unreactive except at elevated temperature (e.g. within the range from 60 to 200°C and usually from 130 to 180°C) at which the printed substrate is cured.

The method may involve the application of an aluminium coating to glass microbeads. The microbeads may be pretreated with stannous chloride prior to application of the aluminium coating, and may be treated with a dilute solution of stannous chloride.

The microbeads may be hemispherically metallised in a vacuum metallising process in which they are held on a film with an adhesive coating for transport through the metallising process, the adhesive coating comprising a styrene/butadiene type or other adhesive, which loses its tack when wet. The film may comprise a polyester or polyolefin film. Following metallisation, the film may be passed through an aqueous solution of citric acid or other aqueous solution with a  $pK_a$  value of around 2, and may be treated ultrasonically to assist in release of the microbeads from the adhesive surface. In contradistinction to other methods for attachment of beads for metallisation, this method is easier at least inasmuch as the citric acid bath can be re-used over and over without replenishment.

The microbeads may be treated prior to inclusion in the ink with a silicate, which may be a dilute aqueous solution of sodium silicate. The beads may also (with or without such sodium silicate treatment) be treated with a silane such as an amino silane prior to inclusion in the ink, and such silane treatment may follow the silicate treatment. A particularly beneficial amino silane is bis- $[\gamma\text{-}(\text{trimethoxysilyl}) \text{ propyl}]$  amine. These treatments, severally and collectively, appear to enhance the permanence of the attachment of the aluminium coating to the microbeads and of the microbeads to the substrate on printing.

An aminoalkyl silanetriol and/or a blocked polyisocyanate may be added to the liquid carrier medium as coupling agent.

In the event, see below, that a two-pack, rather than a one-pack system is required, an alkoxysilyl alkyl derivative such as an amino silane - which could be the same amino silane used to treat the microbeads - and/or a polyisocyanate (typically where the microbeads are amine treated) may also be added to the liquid carrier medium as coupling agent,

In the preparation of the ink, a liquid carrier medium may be prepared comprising binder chemicals and coupling agent, the microbeads being added to the medium. A pigment may be added to the medium containing the microbeads.

Further additive or additives to be incorporated in the liquid carrier medium, may be selected from the group comprising:

pigment; humectant, optionally urea and/or 2,3 propane diol; buffer, optionally based on ammonium or sodium phosphates; dispersant; defoamer; thickening agent; cross-linking agent; softening agent; carbon black; UV absorbing material; anti-scuffing agent, optionally a silicone or fluoropolymer; light spill-suppressing agent; anti-static agent and water repellant agent, optionally a silicone or fluoropolymer.

Where a thickener is included, it may be added to the medium in two steps, namely before and after the addition of the binder and coupler.

According to a further aspect of the invention there is provided microbeads for use in the production of a retroreflective ink, the microbeads having silicate (optionally sodium silicate) and/or silane (optionally an amino silane such as bis-[*gamma*-(trimethoxysilyl) propyl] amino) and/or stannous chloride applied thereto.

The microbeads may be metallised, optionally with a coating of aluminium, the metal being superposed on the stannous chloride.

The microbeads may be metallised, optionally with a coating of aluminium, the silicate and/or silane being superposed on the metallised beads and the silane where present being superposed on the silicate where present.

Also within the scope of the invention is an ink incorporating such microbeads and substrates such as fabrics coated or printed with inks in accordance with the various aspects of the invention.

For certain applications, notably where printed or coated with retroreflective inks, for example for backdrops and special effects screens in film and television studios, it is desirable that fabrics used are fireproof, or fire retardant.

The specialised nature of some retroreflective inks, however, raises problems in connection with many normally fireproof or fire retardant fabric materials.

Another aspect of the invention is concerned with a fireproof or fire retardant fabric printed or coated with retroreflective ink that is particularly satisfactory as a backdrop or screen in the applications in question.

The invention comprises a fireproof or fire retardant fabric printed or coated with a retroreflective ink which comprises retroreflective elements in a polymeric matrix, the fabric comprising a structural component that chars before it melts.

The fabric may be made fireproof or fire retardant by application of a fire retardant agent, such as the commercially available Proban ® or Pyrovatex ®, to cellulose, or it may be naturally fireproof or fire retardant, such as an aramid.

The ink is desirably non-burning, at least once applied to the fabric. The polymeric matrix may comprise polyvinylidene chloride (e.g. in the case of an aqueous-based ink), or polyvinyl chloride or other non-flammable plastisol.

Examples of suitable inks for this purpose are given hereinafter in Tables 2 and 3.

Substrates coated with inks in accordance with various aspects of the present invention may find use in a variety of applications such as flexible tape having a retroreflective coating, for instance tape as used in defining boundary lines and/or cordoning off areas such as crime scenes, construction sites, road works and other hazards.

Another important application is retroreflective materials materials for use as studio background material for chroma-keying and like purposes, as disclosed in GB-A-2312565 and GB-A-2321814 the disclosures of which are incorporated herein by this reference. Thus, a substrate in the form of a flexible sheet material may be coated or printed with an ink in accordance with the present invention to produce a studio background material exhibiting a normalised retro-reflectivity of at least about 1/4 at an angle of incidence of at least 60 degrees to the normal, i.e. as described in GB-A-2312565 and GB-A-2321814.

A substrate provided with a retroreflective coating in accordance with the present invention may be provided with an additional coating or coatings for protecting the retroreflective coating against scuffing and/or moisture (i.e. a water repellant coating), e.g. a fluoropolymer coating applied over the retroreflective coating. An anti-static coating may also be applied to the substrate. Alternatively, instead of coating the substrate with such coatings after printing or coating the substrate with retroflecive ink, the ink may incorporate ingredients which will confer anti-scuffing, water repellant and/or anti-static properties.

The substrate may be selected from a wide range of materials including textile fabrics (e.g. woven or knitted) such as cotton, polyesters, nylons, silk, wool, viscose and acrylics.

Inks and methods for making them, according to the invention, will now be described with reference to the accompanying drawings, in which Figure 1 is a diagrammatic illustration of the production of metallised beads; and Figure 2 is a block diagram of a process for making an ink.

Examples of ink formulations according to the invention are given in Tables 1 to 4.

**Table 1** - Inks based on a acrylic copolymer binder system and (3-aminopropyl) silanetriol coupling agent

<b>Ingredient/Ink reference</b>	<b>C202</b>	<b>C205</b>	<b>C208</b>
Urea (Humectant)	10	10	10
Water	154	179	179
Ammonium phosphate buffer	20	20	20
Alcoprint PDN (Dispersant)	2	2	2
Agitan 218 (Defoamer)	2	2	2
Alcoprint PT21 (Thickening agent)	8	8	8
2,3 Propane diol (Humectant)	25	25	25
Alcoprint PFL (Trimethoxymethyl melamine cross-linking agent)	15	15	15
Alcoprint PSM (Softening agent)	30	30	30
Alcoprint PBA (Acrylic copolymer binder)	300	225	225
Ammonium hydroxide	1	1	1
Silquest VS-142 (3-aminopropyl silanetriol coupling agent)			
[20% in water]	25	25	25
Alcoprint PT21 (Thickening agent)	6	3	4.6
Metallised beads (40 micron) treated with sodium silicate and Silquest A-1170 (Bis[trimethoxysilylpropyl])			

- 12 -

amine)	400	450	400
Nonmetallised beads (40 micron) treated with sodium silicate and Silquest A-1170	--	--	50
<b>Total</b>	997	995	996.6
Binder volume %	12	9	9
Bead volume %	16	18	18
Binder volume/bead volume %	75	50	50
Viscosity	20.7	16.2	23.2
Temperature	16.6	16.6	16.6
pH	8.4	8.9	8.8



**Table 2** - Inks based on a polyvinylidene chloride copolymer binder system and (3-aminopropyl) silanetriol coupling agent

<b>Ingredient/Ink reference</b>	<b>V246</b>	<b>V248</b>	<b>V251</b>
Urea (Humectant)	10	10	10
Water	128	288	288
Ammonium phosphate buffer	20	20	20
Emulsifier WN (Dispersant)	3	3	3
Agitan 218 (Defoamer)	2	2	2
Alcoprint PT21 (Thickening agent)	8	8	8
2,3 Propane diol (Humectant)	25	25	25
Polidene 33-048 (Binder)	273	163	163
Ammonium hydroxide	1.4	1.4	1.4
Silquest VS-142 (Coupling agent) [20% in water]	25	25	25
Alcoprint PT21 (Thickening agent)	3	5	3
Metallised beads (40 micron) treated with sodium silicate and Silquest A-1170	500	450	400
Non-metallised beads (40 micron) treated with sodium silicate and Silquest A-1170	--	--	50
<b>Total Weight of Ink (g)</b>	<b>998.4</b>	<b>1,000.4</b>	<b>998.4</b>
Binder volume %	15	9	9
Bead volume %	20	18	18
Binder volume/bead volume %	75	50	50
Viscosity (pascals)	25.6	14.2	12.3
Temperature (°C)	17.7	17.6	17.2
pH	8.6	8.7	8.7

**Table 3 -** Inks based on a polyvinylidene copolymer binder system and a combination of (3-aminopropyl) silanetriol and blocked hexamethylene diisocyanate trimer coupling agents

<b>Ingredient/Ink reference</b>	<b>V253</b>	<b>V254</b>	<b>V257</b>
Urea (Humectant)	10	10	10
Water	91	183	183
Ammonium phosphate buffer	20	20	20
Emulsifier WN (Dispersant)	2	2	2
Emulsifier HVN (Dispersant)	2	2	2
Agitan 218 (Defoamer)	2	2	2
Alcoprint PT21 (Thickening agent)	9.3	8	8
2,3 Propane diol (Humectant)	25	25	25
Polidene 33-048 (Binder)	273	181	181
Ammonium hydroxide	1.4	1.4	1.4
Silquest VS-142 (Coupling agent) [20% in water]	25	25	25
Trixene BI 7986 (Coupling agent)	40	40	40
Alcoprint PT21 (Thickening agent)	--	--	--
Metallised beads (40 micron) treated with sodium silicate and Silquest A-1170	500	500	400
Non-metallised beads treated with sodium silicate and Silquest A-1170	--	--	100
<b>Total Weight of Ink (g)</b>	<b>1,000.7</b>	<b>999.4</b>	<b>999.4</b>
Binder Volume %	15	10	10
Bead Columes %	20	20	20
Binder Volume/Bead Volume Ratio %	75	50	50
Viscosity (pascals)	22.5	22.1	21.2
Temperature (°C)	19.3	19.0	19.0
pH	8.4	8.3	8.4

**Table 4** - Inks based on a polyurethane binder system and a blocked 1,6 Hexamethylene diisocyanate trimer coupling agent

<b>Ingredient/Ink reference</b>	<b>P96</b>	<b>P98</b>	<b>P102</b>
Urea (Humectant)	10	10	10
Water	62	187	187
Sodium Phosphate Buffer	10	10	10
Emulsifier WN (Dispersant)	3	3	3
Agitan 218 (Defoamer)	2	2	2
Alcoprint PT21 (Thickener)	3.0	3.1	3.0
2,3 Propane diol (Humectant)	25	25	25.1
Alcoprint PSM (Softener)	30	30	30
Witcobond 769 (Binder)	300	225	226
Trixene BI-7986 (Coupler)	50	50	50
Alcoprint PT21 (Thickener)	0.7	4.0	3.0
Metallised beads treated with sod.silicate and Silquest A-1170	500	450	400
Non-metallised beads treated with sod.silicate and Silquest A-1170	--	--	70
<b>Total Weight of Ink (g)</b>	<b>993.7</b>	<b>999.1</b>	<b>1,019.1</b>
Binder Volume %	12	9	8.8
Bead Volume %	60	18	18.5
Binder Volume/Bead Volume Ratio %	60	50	47.9
Viscosity (pascals)	O/R	31.0	32.0
Temperature (°C)	18.8	18.2	18.5

Generally speaking, the ingredients are added in the tabulated order given in Tables 1 to 4. The thickener is added in two stages. Pigment, not tabulated, is added at the end in suitable quantity to yield the desired colour.

Viscosities were measured with a Brookfield viscometer using a number 5 spindle rotating at 10 rpm.

Table 5 lists the chemical nature and sources of proprietary products used in the inks of Tables 1 to 4.

**Table 5**

<b>Ink Component</b>	<b>Proprietary Product</b>	<b>Chemical Nature</b>	<b>Supplier</b>
<b>Binder</b>	Alcoprint PBA	Aqueous emulsion of an acrylic copolymer	Allied Colloids
	Polidene 33-048	Aqueous emulsion of a vinylidene chloride/acrylate copolymer	Scott Bader
	Witcobond 769	Water based polyurethane dispersion	Baxenden
<b>Cross-linking/ coupling agent</b>	Alcoprint PFL	Trimethoxymethyl melamine	Allied Colloids
	Silquest VS-142	3-Aminopropyl silanetriol	OSi Specialities/ Ambersil Ltd.
	Silquest A-1170	bis-trimethoxysilylpropyl) amine	OSi Specialities/ Ambersil Ltd.
	Trixene BI-7986	Blocked 1,6 hexamethylene diisocyanate trimer	Baxenden
<b>Softening agent</b>	Alcoprint PSM		Allied Colloids
<b>Thickening agent</b>	Alcoprint PT21	Dispersion of an acrylic copolymer in light mineral oil	Allied Colloids
<b>Dispersant</b>	Alcoprint PDN	Aqueous solution of an anionic acrylic polymer	Allied Colloids
	Emulsifier WN	Nonionic arylpolyglycol ether	Bayer

- 17 -

<b>Ink Component</b>	<b>Proprietary Product</b>	<b>Chemical Nature</b>	<b>Supplier</b>
	Emulsifier HVN		BASF
Defoaming agent	Agitan 218		Munzing Chemie

Retroreflective microbeads are made, according to one aspect of the invention, by a process which is generally similar to the one that has been used commercially for many years, namely by embedding glass microspheres in an adhesive layer on a substrate and coating the exposed surface of the microspheres with an aluminium layer in a vacuum metalliser. There are, however, subtle, but important differences. The method according to the invention, which is novel and inventive *per se* for the manufacture of hemispherically coated microbeads, regardless of any ink formulation in which they will be used is illustrated by way of example in Figure 1.

A carrier material 11, which is for example a polyester film, supplied on a reel 11a, which may contain, say, 1000m of film of width 1500mm, is coated by contact with a lick roller 12 dipping into a bath 13 with an 18 micron layer 14 of a styrene/butadiene type adhesive 15, the coating thickness being determined e.g. by a doctor blade/roller arrangement 16.

Beads 17 (see inset to Figure 1) are scattered on the adhesive layer 14 from a hopper 18 and pressed into the adhesive layer 14 by a roller arrangement 19. Excess beads are removed e.g. by suction arrangement 20.

Glass beads of refractive index 1.9, size 40 microns are used, and, after the roller arrangement 19, appear, in cross-section, as shown in the inset.

The beaded carrier material 11 is then passed through a vacuum metalliser 21 to be coated with aluminium to a thickness of about 0.3 microns. The material 11, wound on a reel, is placed in the vacuum metalliser and run off on to a take-up reel to which it is secured; then the metalliser is evacuated and the aluminium source energised and the material passed reel-to-reel to expose it to the aluminium vapour. The coated, beaded carrier 11 is then passed through a bath 22 of aqueous solution (1%) of citric acid at a temperature of 40 - 50°C, passing over a series of rollers 23 to provide a dwell time in the bath of several minutes. The material 11 also passes over an ultrasonic plate 24 which aids release of the microbeads which fall to the bottom of the bath 22. At the end of the run of 1000m of carrier 11, the microbeads are sucked out of the bottom of the bath 22, rinsed with water and dried.

The effect of the citric acid bath is to cause the styrene/butadiene adhesive to lose its tack and release the microbeads. The material 11 regains its tack on drying, and can be re-used for further runs of bead manufacture without the need for further coating. The citric acid bath 22 can likewise be reused without replenishment of the citric acid.

Prior to coating, the glass beads are pre-treated with a dilute aqueous solution of stannous chloride, followed by drying and resieving. It is found that this gives significant improvement in the durability of the reflectivity of a printed design.

After coating, the beads are treated with a dilute aqueous solution of sodium silicate. It is thought that the treatment passivates the aluminium coating, reducing its susceptibility to attack in aqueous environments, while, at the same time, the sodium silicate reacts with the titanium/barium glass and/or the aluminium increasing the number of reactive sites on the surface of the coated microbeads that are available for reaction with the coupling agent in the ink.

If this sodium silicate treatment is carried out close to the metallisation process, the beads from that process can be used after rinsing but before drying. About 40 kg wet metallised beads (containing some 10 kg water) are mixed with a solution of 20 kg water containing 1.4 kg sodium silicate and stirred for 5 minutes. The beads are then allowed to settle, the sodium silicate solution decanted off, the beads rinsed with tap water, with a final rinse in deionised water.

Significant improvement in washfastness, especially with low (e.g. below 0.5%) levels of certain coupling agents in the formulation (which considerably improves shelf life), is obtained by further treatment of the metallised beads with amino silanes, significantly bis-*[gamma*-(trimethoxysilyl) propyl] amine.

The combined effect of these bead preparation treatments is to provide an ink with a shelf life well in excess of 12 months yet which exhibits insignificant loss of retroreflectivity after multiple washings at 40°C, even if the amount of coupling agent is as low as 0.5%.

Figure 2 is a block diagram of production steps for a typical ink according to the invention, the steps being :

- 30 Glass microbead production, with any necessary sieving to a desired size range - about 40 microns is an ideal size;
- 31 Stannous chloride pre-treatment, drying;
- 32 Metallising;
- 33 Recovery in citric acid solution;
- 34 Rinsing;
- 35 Drying;
- 36 Sodium silicate treatment of metallised beads;

- 20 -

- 37 Rinsing;
- 38 Amino silane pre-treatment;
- 39 Mixing liquid carrier medium;
- 40 Add treated metallised (and, if desired, umetallised) beads to carrier medium;
- 41 Add pigment;

Ink formulations detailed herein, formulated by the methods described, operating as one-pack systems, have long shelf lives, being usable after more than six months, in many cases after more than a year after formulation (based on accelerated ageing measurements at elevated storage temperatures). They show higher initial retroreflectivities at the lower binder/bead volume ratios made possible by the various measures described.

Washfastness and abrasion resistance are acceptable with binder volumes as low as 9% - reducing binder content in the formulation containing polyvinylidene chloride and Trixene actually increases abrasion resistance.

The various novel ingredients and combinations of ingredients each have their contributions to make in connection with the production of one pack inks and while the importance of a binder combined with a coupling agent reacting only at elevated temperature has been particularly noted, it is not intended to suggest that that might be the only novel and inventive subject matter disclosed herein. The pre-treatment of the beads both before and after metallisation also has profound effects even with the binder/coupler systems and is of advantage also in the preparation of inks for printing on substrates which will not withstand elevated temperatures. Here it is necessary to resort to a two-pack system, with the coupling agent mixed into the ink just before printing. A reactive polyisocyanate may be used as a coupling agent in such circumstances. A



two-pack arrangement is, of course, more convenient to use than the old three-pack system, and is made possible by bead pre-treatment.

Where unmetallised beads are added - giving the effect, quite obviously, of reducing overall retroreflectivity, but reducing the greyness associated with metallised beads and therefore enhancing the colour brightness of pigmented inks, the unmetallised beads also benefit from the bead pre-treatment, particularly treatment with silicate and silane. .

Unmetallised beads may also be used in similar formulation, and having had similar pre-treatment, without metallised beads but with flake particles having a mirror-like finish. Such a coating composition, said to be suitable for application by brushing, was described in US 3 835 087, Searight *et al*, issued 10 September 1974, and printing ink of this description is commercially available.

According to the present invention, in another aspect, one-pack inks containing unmetallised glass microspheres and flake particles comprise a liquid carrier medium including binder chemicals for attaching the microbeads and flake particles to a substrate to which the ink is to be applied and a coupling agent which couples the microbeads and cross-links the binder chemicals, characterised in that the coupling agent is unreactive except at elevated temperature at which the ink of the substrate is cured.

Binder and coupler systems as described above are suitable, and the microbeads benefit in the same way from the sodium silicate and amino silane pre-treatment - the stannous chloride pre-treatment is unnecessary.

- 22 -

A preferred flake material is Iriodin 123 - mica flake coated with titanium dioxide, supplied by Merck. The optimum particle size is 5-35 microns, and the flake may be present in an amount about 7.5% by weight.

Mean glass microbead size may be 60 micron - larger beads, e.g. up to 70 micron and larger may be used but may not be suitable for finer screen printing mesh sizes. Good quality, e.g. 1.9 refractive index, beads give better results than lower refractive index beads, and best results are obtained using 60 micron TSTF (twice sieved twice fired) beads.

Coloured reflectivity can be achieved by using interference pigments (Iriodin 200 series), while gold lustre mica pigments (Iriodin 300 series) and metal lustre pigments (Iriodin 500 series) give interesting effects particularly when printed on coloured fabrics.

Table 6 lists ingredients for a range of such inks.

**Table 6**

<b>Ingredient/Ink reference</b>	<b>NMB155</b>	<b>NMB182</b>	<b>NM B185</b>	<b>NMB191</b>
Urea (Humecant)	10	10	10	10
Water	79	134	94	91
Ammonium phosphate buffer	20	20	20	--
Sodium phosphate buffer	--	--	--	10
Emulsifier WN (Dispersant)	--	3	2	3
Emulsifier HVN (Dispersant)	--	--	2	--
Alcoprint PDN (Dispersant)	2	--	--	--
Agitan 218 (Defoamer)	2	2	2	2
Alcoprint PSM (Softener)	30	--	--	30
Alcopriny PT21 (Thickener)	4	4.8	3.3	3
2,3 Propane diol (Humectant)	25	25	25	25
Alcoprint PFL (Cross-linker)	15	--	--	--
Alcoprint PBA (Binder)				
[acrylic]	300	--	--	--
Polidene 33-048 (Binder)				
[polyvinylidene chloride]	--	300	300	--
Witcobond 769 (Binder)				
[polyurethane]	--	--	--	300
Trixene BI-7986 (Coupling agent)	--	--	40	50
Ammonium hydroxide	1	1.4	1.4	--
Silquest VS-142 (Coupling agent) [20% in water]	25	25	25	--
Alcoprint PT21 (Thickener)	3.5	--	--	1
Iriodin 123 [Mica coated with titanium dioxide]	75	75	75	75
Beads (60 micron) treated with sod.sil.+ A-1170	400	400	400	400
<b>Total weight (g)</b>	<b>991.5</b>	<b>1000.2</b>	<b>999.7</b>	<b>1000.0</b>
Viscosity (pascals)	23.6			
pH	8.5			

CLAIMS

1. The combination of ingredients, especially for use in the formulation of a one or two-pack retroreflective ink, comprising retroreflective elements, microbeads additional to said retroreflective elements and/or constituting said retroreflective elements at least in part, binder chemicals for attaching the retroreflective elements and microbeads to a substrate to which the ink is to be applied, and a coupling agent for coupling the microbeads and cross-linking the binder chemicals, the coupling agent being unreactive until the printing process is carried out.
2. The combination of Claim 1 in which the coupling agent is unreactive except at elevated temperature at which the printed substrate is cured.
3. The combination of Claim 1 or 2, at least some of the microbeads being without a retroreflective coating.
4. The combination of Claim 1, 2 or 3 in which the binder/coupling agent system is selected from the group comprising:
  - polyvinylidene chloride copolymer as binder and (3-aminopropyl) silanetriol and/or blocked 1, 6 hexamethylene diisocyanate trimer as coupling agent;
  - an acrylic copolymer as binder and (3-aminopropyl) silanetriol and/or blocked 1, 6 hexamethylene diisocyanate trimer as coupling agent; and
  - polyurethane as binder and blocked 1, 6 hexamethylene diisocyanate trimer as coupling agent.
5. The combination of any one of Claims 1 to 3 further comprising one or more components selected from the group comprising:

pigment; humectant, optionally urea and/or 2,3 propane diol; buffer, optionally based on ammonium or sodium phosphates; dispersant; defoamer; thickening agent; cross-linking agent; softening agent; carbon black; UV absorbing material; anti-scuffing agent, optionally a silicone or fluoropolymer; light spill-suppressing agent; anti-static agent and water repellant agent, optionally a silicone or fluoropolymer.

6. The combination of any one of Claims 1 to 5 in which the binder volume to bead volume ratio is equal to or less than 50%.

7. The combination of any one of Claims 1 to 6 in which the microbeads are all or essentially all unmetallised and the retroreflective elements comprise reflective flake particles.

8. The combination of any one of Claims 1 to 7 in which the binder forms at least part of a liquid carrier medium in which the retroreflective elements and/or microbeads are incorporated.

9. The combination as claimed in any one of Claims 1 to 7 in which the binder chemicals and retroreflective elements/microbeads comprise one pack retroreflective ink or a two-pack retroreflective ink with the coupling agent comprising the second pack.

10. The combination of Claim 9, being a two pack ink in which the coupling agent comprises a reactive polyisocyanate and/or an alkoxysilyl alkyl derivative.

11. The combination of any one of Claims 1 to 10, the microbeads having silicate (optionally sodium silicate) and/or silane (optionally an amino silane such as bis-[*gamma*-(trimethoxysilyl) propyl] amino) and/or stannous chloride applied thereto.

12. The combination of Claim 11 in which the microbeads are metallised, optionally with a coating of aluminium, the metal being superposed on the stannous chloride.

13. The combination of Claim 11 or 12 in which the microbeads are metallised, optionally with a coating of aluminium, the silicate and/or silane being superposed on the metallised beads and the silane where present being superposed on the silicate where present.

14. A one or two-pack retroreflective ink comprising the combination claimed in any one of Claims 1 to 13.

15. An ink as claimed in Claim 14, being water-based.

16. An ink as claimed in Claim 14 or 15, formulated suitably for screen printing.

17. An ink as claimed in Claim 14, 15 or 16 of which the viscosity is less than or equal to 40 pascals, preferably between 10 and 30 pascals, at room temperature.

18. Microbeads for use in the production of a retroreflective ink, the microbeads having silicate (optionally sodium silicate) and/or silane (optionally an amino silane such as bis-*[gamma]*-(trimethoxysilyl) propyl] amino) and/or stannous chloride applied thereto.

19. Microbeads as claimed in Claim 18 which are metallised, optionally with a coating of aluminium, the metal being superposed on the stannous chloride.

20. Microbeads as claimed in Claim 18 or 19 which are metallised, optionally with a coating of aluminium, the silicate and/or silane being superposed on the metallised beads and the silane where present being superposed on the silicate where present.

21. Microbeads as claimed in any one of Claims 18 to 20 having one or more of the following characteristics: a refractive index in the range of 1.8 to 2.2, preferably about 1.9; in the form of beads having a median size in the range of 10 to 100 microns, preferably 25 to 70 microns; and composed of titanium/barium glass.

22. A retroreflective ink containing microbeads as claimed in any one of Claims 18 to 21

23. An ink as claimed in Claim 22 including binder chemicals for attaching the microbeads to a substrate to which the ink is to be applied.

24. An ink as claimed in Claim 23 including a coupling agent for coupling the microbeads and cross-linking the binder chemicals, the coupling agent being unreactive until the printing process is carried out.

25. A method for making a one-pack retroreflective ink comprising the steps of:

- making microbeads;
- suspending the microbeads in a liquid carrier medium;
- the liquid carrier medium comprising binder chemicals for attaching the microbeads to a substrate to which the ink is to be applied and a coupling agent which couples the microbeads and cross-links the binder chemicals, the coupling agent being unreactive except at elevated temperature at which the printed substrate is cured.

26. A method according to Claim 25, comprising applying an aluminium coating to the microbeads.
27. A method according to Claim 26, comprising pre-treating the microbeads with stannous chloride prior to application of the aluminium coating.
28. A method according to Claim 27, in which the microbeads are treated with a dilute aqueous solution of stannous chloride.
29. A method according to any one of Claims 25 to 28, in which the microbeads are hemispherically metallised in a vacuum metallising process in which they are held on a film, optionally a polyester or polyolefin film, with an adhesive coating for transport through the metallising process, the adhesive coating comprising a styrene/butadiene type adhesive.
30. A method according to Claim 29 in which, following metallisation, the film is passed through an aqueous solution of citric acid.
31. A method according to Claims 29 or 30 in which the film is treated ultrasonically to assist in release of the microbeads from the adhesive surface.
32. A method according to any one of Claims 28 to 31 in which the microbeads are treated prior to inclusion in the ink with a silicate, optionally a dilute aqueous solution of sodium silicate.
33. A method according to any one of Claims 25 to 32 in which the microbeads are treated with a silane, preferably an amino silane, prior to inclusion in the ink.



34. A method according to Claim 32 or Claim 33 when dependent on Claim 29 in which the microbeads are treated with the silane, optionally an amino silane such as bis-[*gamma*-(trimethoxysilyl) propyl] amine, following the silicate treatment.

35. A method according to any one of Claims 25 to 34 in which an amino silanetriol, e.g. an amino silane, and/or a blocked polyisocyanate is added to the liquid carrier medium as coupling agent.

36. A method according to any one of Claims 25 to 35, in which a liquid carrier medium is prepared comprising binder chemicals and coupling agent, and the microbeads are added to the medium.

37. A method according to Claim 36, in which a further additive or additives are incorporated in the liquid carrier medium, said additives being selected from the group comprising:

pigment; humectant, optionally urea and/or 2,3 propane diol; buffer, optionally based on ammonium or sodium phosphates; dispersant; defoamer; thickening agent; cross-linking agent; softening agent; carbon black; UV absorbing material; anti-scuffing agent, optionally a silicone or fluoropolymer; light spill-suppressing agent; anti-static agent and water repellant agent, optionally a silicone or fluoropolymer.

38. A method according to Claim 37, in which a thickener is added to the liquid carrier medium in two steps, namely before and after the addition of the binder and coupler.

39. An ink produced by the method of any one of Claims 25 to 38.

40. A substrate coated or printed with ink as claimed in any one of Claims 14 to 17, 22 to 24 and 39.
41. A substrate as claimed in Claim 40 in the form of a screen for displaying projected images or a studio background for chroma-keying applications.
42. A substrate as claimed in Claim 40 in the form of flexible tape.
43. A method of providing a substrate with a retroreflective coating comprising applying to the substrate an ink as claimed in any one of Claims 14 to 17, 24 and 39, the ink having been formulated as a one-pack ink and the coupling agent being activated after the ink has been printed or coated on to the substrate.
44. A method as claimed in Claim 43 in which the coupling agent is activated by curing of the ink coating at elevated temperature.
45. A method as claimed in Claim 43 in which the coupling agent is activated by UV light or other high energy radiation during and/or after the printing process.
46. A retroreflective one-pack ink with a storage life of not less than 3 months, preferably not less than 6 months and more preferably not less than 12 months.
47. A retroreflective one-pack ink which has a viscosity of between 10 and 30 pascal after storage after storage for not less than 3 months, preferably not less than 6 months and more preferably not less than 12 months.
48. A retroreflective one-pack ink which has laundering durability such that retroreflectivity is not reduced by more than 40% (preferably by not more than 30%,

more preferably by not more than 20%) when applied to a substrate in the form of a cotton, nylon or polyester fabric and laundered for 5 cycles in accordance with ISO 6330, method 5A.

49. A fireproof or fire retardant fabric printed or coated with a retroreflective ink which comprises retroreflective elements in a polymeric matrix, the fabric comprising a structural component that chars before it melts.

50. A fabric according to claim 49 made fireproof or fire retardant by application of a fire retardant agent.

51. A fabric according to claim 50 in which the fire retardant agent comprises Proban ® or Pyrovatex ® or a like agent, applied to a cellulosic.

52. A fabric according to any one of Claims 49 to 52, the fabric comprising an aramid fibre.

53. A fabric according to any one of Claims 49 to 52, in which the ink is non-burning once applied to the fabric.

54. A fabric according to claim 53, in which the ink is aqueous-based and the polymeric matrix comprises polyvinylidene chloride.

55. A fabric according to claim 53, in which the polymeric matrix comprises polyvinyl chloride or other non-flammable plastisol.

56. A fabric as claimed in any one of Claims 49 to 55 in which the ink comprises an ink as claimed in any one of Claims 1 to 17, 22 to 24, 39 or 46 to 48.

**THIS PAGE BLANK (USPTO)**



**This Page Blank (uspto)**

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 00/00062

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09D11/02

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09D 602B C03C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 97 12284 A (MINNESOTA MINING & MFG) 3 April 1997 (1997-04-03) page 1, line 10-15 page 8, line 7-15 page 22, line 8-13	1,2
A	GB 2 316 021 A (TRIP PRODUCTIONS B V) 18 February 1998 (1998-02-18) the whole document	
A	US 5 650 213 A (RIZIKA DANIEL J ET AL) 22 July 1997 (1997-07-22) cited in the application	
	-/-	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

### \* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

13 April 2000

Date of mailing of the international search report

20/04/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Miller, A

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 00/00062

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 95 14248 A (REFLECTIVE TECHNOLOGY IND LTD ;SAGAR BRIAN (GB); MOULE ROBERT (GB)) 26 May 1995 (1995-05-26)	
A	& EP 0 729 592 A (REFLECTIVE TECHNOLOGY INDUSTRIES LIMITED) 4 September 1996 (1996-09-04) cited in the application	



# INTERNATIONAL SEARCH REPORT

Information on patent family members

Inter. Application No

PCT/GB 00/00062

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9712284	A	03-04-1997	EP 0852745 A JP 11513422 T US 5886067 A	15-07-1998 16-11-1999 23-03-1999
GB 2316021	A	18-02-1998	NL 1006745 C NL 1006745 A	02-11-1999 12-02-1998
US 5650213	A	22-07-1997	AU 4464196 A CN 1168724 A EP 0795138 A GB 2310863 A, B JP 10510930 T WO 9617264 A	19-06-1996 24-12-1997 17-09-1997 10-09-1997 20-10-1998 06-06-1996
WO 9514248	A	26-05-1995	AU 1032595 A EP 0729592 A JP 9506301 T US 5900978 A	06-06-1995 04-09-1996 24-06-1997 04-05-1999

**This Page Blank (uspto)**